

SPECIFICATION

PROPERTIES

Specifications	Premium Grade			Test Method
	LX-C3R	LX-C3Y	LX-G1R	
	Natural Color	Natural Color	Natural Color	
Mooney Viscosity ML (1+4) 100°C	55.0-80.0	65.0-90.0	35.0-65.0	ISO 289 - 1
Specific Gravity (g/cm ³)	0.8-1.0	0.8-1.0	1.0-1.05	HG/T2728
After Vulcanizing				
Tensile Strength (MPa)	10.00-14.00	11.00-14.50	11.00-14.50	ISO 37 (Type1)
Modulus at 300% Elongation (MPa)	1.00-3.00	1.00-3.00	1.00-3.00	ISO 37 (Type1)
Elongation at Break (%)	650-850	700-900	700-900	ISO 37 (Type1)

Remarks : 1. Sample characteristics: REFINED RUBBER (EKO RUBBER)
2. This test report shall not be reproduced in all case without the permission.

Packing: Net 20 kg./bale wrapped with LDPE or EVA Plastic

Update: 22 March 2016