

## SPECIFICATION

### PROPERTIES

Specifications	High Grade			Test Method
	NR-NMB	NR-NMG	NR-NPB	
	Blue Color	Green Color	Blue Color	
Mooney Viscosity ML (1+4) 100°C	30.0-60.0	30.0-60.0	35.0-65.0	ISO 289 - 1
Specific Gravity (g/cm <sup>3</sup> )	1.00-1.10	1.00-1.10	1.00-1.10	HG/T2728
After Vulcanizing				
Tensile Strength (MPa)	7.50-8.99	7.50-8.99	9.00-9.99	ISO 37 (Type1)
Modulus at 300% Elongation (MPa)	2.00-4.00	2.00-4.00	2.00-4.00	ISO 37 (Type1)
Elongation at Break (%)	480-680	480-680	500-620	ISO 37 (Type1)

Remarks: 1. Sample characteristics: REFINED RUBBER (EKO RUBBER)  
2. This test report shall not be reproduced in all case without the permission.

Packing : Net 20 kg./bale wrapped with HDPE Plastic

Update : 22 March 2016